

FlexFoam-iT!® Series

Flexible Polyurethane Foams

3lb., 4 lb., 5lb., 6 lb., 7 lb., 8 lb., 10 lb., 14 lb., 17 lb. or 25 lb.



www.smooth-on.com

PRODUCT OVERVIEW

FlexFoam-iT!® Series foams are premium quality water blown flexible foams that can be used for a variety of industrial, special effects and art & crafts and projects. With several to choose from, uses include making theatrical props (swords, knives, hammers, etc.), industrial gaskets, custom padding and cushioning, and more. SO-Strong® colorants can be added for color effects.

Part A and B liquids are combined, mixed and poured into a mold or other form (apply release agent if necessary). Mixture will rise and cure quickly to a solid, flexible foam. Foams vary by density and offer good physical properties. The lower the number, the more the foam expands. FlexFoam-iT!® III is the lowest density foam and expands the most. FlexFoam-iT!® 25 is the highest density foam and expands the least. FlexFoam-iT!® 7 FR certifies to FMVSS-302 Flame Specification.

8oz./237ml. of FlexFoam-iT!® A+B poured into a 32oz./946ml. cup.



TECHNICAL OVERVIEW

	A:B Mix Ratio by Volume	A:B Mix Ratio by Weight	Specific Gravity (g/cc) (ASTM D-1475)	Specific Volume (cu. in./lb.)	Pot Life (Cream Time) (ASTM D-2471)	Tack-Free Time	Approximate Volumetric Expansion	Lbs. / Cu. Foot = Kgs. / Cu. Meter
FlexFoam-iT!® III	1:2 pbv	57.5:100 pbw	0.06	400-450	35 sec	25 min.	15 times	3 lb/ft ³ = 48 kg/m ³
FlexFoam-iT!® IV	N/A	80:100 pbw	0.08	275-300	30 sec	20 min.	10 times	5 lb/ft ³ = 80 kg/m ³
FlexFoam-iT!® V	1:1 pbv	105:100 pbw	0.10	275-300	50 sec	25 min.	10 times	5 lb/ft ³ = 80 kg/m ³
FlexFoam-iT!® 6	1:1 pbv	105:100 pbw	0.12	275-300	35 sec	2 hrs.	10 times	5 lb/ft ³ = 80 kg/m ³
FlexFoam-iT!® 7 FR	1:1 pbv	100:88 pbw	0.11	240-260	35 sec	2 hrs.	8 times	7 lb/ft ³ = 110 kg/m ³
FlexFoam-iT!® VIII	1:2 pbv	52.6:100 pbw	0.13	175-225	35 sec	25 min.	8 times	8 lb/ft ³ = 128 kg/m ³
FlexFoam-iT!® X	1:1 pbv	105:100 pbw	0.18	150-200	50 sec	25 min.	6 times	10 lb/ft ³ = 160 kg/m ³
FlexFoam-iT!® 14	1:2 pbv	100:190 pbw	0.22	115-135	60 sec	25 min.	4 times	14 lb/ft ³ = 220 kg/m ³
FlexFoam-iT!® 17	1:2 pbv	100:185 pbw	0.27	95-103	60 sec	25 min.	3.5 times	17 lb/ft ³ = 270 kg/m ³
FlexFoam-iT!® 25	N/A	1:2 pbw	0.4	50-75	50 sec	25 min.	2 times	25 lb/ft ³ = 400 kg/m ³

Mixed Viscosity (ASTM D-2393): 1000 cps

Color: White

Handling Strength: 30 Minutes

Cure Time: 2 Hours

* Values measured at room temperature (73°F/23°C)

PROCESSING RECOMMENDATIONS

PREPARATION...

Preparation - Store and use at room temperature (73°F/23°C). Environmental humidity should be as low as possible. Good ventilation (room size) is essential. This product has a limited shelf life and should be used as soon as possible. Wear safety glasses, long sleeves and rubber gloves to minimize contamination risk. Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.

IMPORTANT: Shelf life of product is reduced after opening. Remaining product should be used as soon as possible. Immediately replacing the lids on both containers after dispensing product will help prolong the shelf life of the unused product. XTEND-IT® Dry Gas Blanket (available from Smooth-On) will significantly prolong the shelf life of unused liquid urethane products.

Safety First!

The Material Safety Data Sheet (MSDS) for this or any Smooth-On product should be read prior to use and is available upon request from Smooth-On. All Smooth-On products are safe to use if directions are read and followed carefully.

Keep Out Of Reach Of Children.

Be careful. Part A (Yellow Label) contains methylene diphenyldiisocyanate. Vapors, which can be significant if heated or sprayed, may cause lung damage and sensitization. Use only with adequate ventilation. Contact with skin and eyes may cause severe irritation. Flush eyes with water for 15 minutes and get immediate medical attention. Remove from skin with soap and water.

Part B (Blue Label) is irritating to the eyes and skin. Avoid prolonged or repeated skin contact. If contaminated, flush eyes with water for 15 minutes and get immediate medical attention. Remove from skin with soap and water. When mixing with Part A, follow precautions for handling isocyanates. If machining cured FlexFoam-It!®, wear dust mask or other apparatus to prevent inhalation of residual particles.

Important: The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe a copyright or patent. User shall determine suitability of the product for the intended application and assume all associated risks and liability whatsoever in connection therewith.

the mold opening the holes are over the mold cavity and rising foam will be able to make it through. Apply Ease Release® 2831 thoroughly to both sides of the board and into the drilled holes. Mix and pour FlexFoam-It!® into mold cavity and place board over mold opening. Secure board firmly in place (mold straps may be necessary). As foam rises in the mold cavity, some foam will grow out of the drilled holes. After the foam stops growing, you can let go of the board. Do not handle for at least 30 minutes. After 30 minutes, you can then cut excess material that came through holes and gently remove board and casting.

Is Your Foam Collapsing? - This is a common phenomenon associated with cold temperatures, inadequate mixing or both. **Environment or material too cold?** Warm it up. **Inadequate mixing?** You must thoroughly pre-mix both parts A and B. After combining A and B, mix thoroughly. If using a mechanical mixer, mix for 30 seconds. When hand mixing, mix quickly and aggressively, almost whipping the material.

APPLYING A RELEASE AGENT...

Urethane foams are adhesive and will stick / bond to many surfaces. **We recommend Ease Release 2831 to release urethane foam from most surfaces.** If the release application is particularly difficult (example; releasing urethane foam from urethane rubber), we recommend an application of Universal Mold Release followed by an application of Ease Release 2831. **WARNING;** Do not use Universal Mold Release by itself, or any other silicone based release agents. This will collapse the foam.

IMPORTANT: To ensure thorough coverage, lightly brush the release agent with a soft brush over all surfaces. Let the release agent dry for 30 minutes.

PRE-MIXING & MIXING...

Pre-mix Parts A & B – Stir or shake both Part A & Part B thoroughly before dispensing.

Measuring – Stop! Know the mix ratio of the foam product you are using. Some are by weight and some are by volume. Dispense the correct amounts of Part A and Part B into a large mixing container.

For Best Results - Pre-Mix Part B after measuring out material – although not necessary, pre-mixing Part B using a drill and mechanical mixer (such as a turbine mixer available from Smooth-On) after measuring out and before combining with Part A will yield best results.

For Best Results - Use a Mechanical Mixer – Mix for 30 seconds and pour into mold or form.

Mixing by Hand – Stir quickly and deliberately for 30 seconds. Make sure that you aggressively scrape the sides and bottom of your mixing container several times. Pour into mold or form.

Be careful not to splash low-viscosity liquid out of container. Remember, these materials cure quickly. Do not delay between mixing and pouring.

POURING, CURING & PERFORMANCE...

Pouring & Curing - For best results, pour your mixture in a single spot at the lowest point of the containment field and let the mixture seek its level. Allow space in the containment field for the foam to grow as it expands to its ultimate volume. Allow foam to cure for at least 30 minutes before handling.

Improving Surface Finish & Minimizing Voids With Back Pressure - Use a board that will completely cover the mold opening. Using a 3/4" (2 cm) drill bit, drill 3 holes in the board spaced a few inches/cm apart. Make sure that when the board is placed over



Call Us Anytime With Questions About Your Application

Toll-free: (800) 381-1733 Fax: (610) 252-6200

The new www.smooth-on.com is loaded with information about mold making, casting and more.

062314-JR